

QUADRANT EPP PRODUCT DATA SHEET

June 2001

NYLATRON® NSM

Cast Nylon 6 (PA6G, Internally Lubricated)

NYLATRON® NSM is a proprietary cast nylon 6 containing solid lubricant additives giving the material self-lubrication, excellent friction properties, superior wear resistance and outstanding Pressure - Velocity capabilities.

- Good chemical resistance (pH 5-11)
- Self lubricating
- Excellent wear resistance
- Dark grey colour
- Continuous temperature 90°C (max. 165°C)
- High stiffness/strength
- Low weight (1/6 Vs steel)
- Excellent dynamic bearing material

Common applications: Bearings; Thrust washers; Slides.

Delivery Programme

Rod 3m long		
Diameter (mm):	50 (Min)	150 (Max)
Rod 1m long		
Diameter (mm):	50 (Min)	500 (Max)
Rod 500mm long		
Diameter (mm):	210 (Min)	500 (Max)
Plate		
Thickness (mm):	10 (Min)	100 (Max)
Sizes (mm):	610 x 1220, 1220 x 2000 1220 x 2440	
Tube 2m long		
O.D. (mm):	50 (Min)	150 (Max)
I.D. (mm):	20 (Min)	135 (Max)
Tube 1000mm long		
O.D. (mm):	155 (Min)	260 (Max)
I.D. (mm):	50 (Min)	235 (Max)
Tube 600mm long		
O.D. (mm):	220 (Min)	600 (Max)
I.D. (mm):	70 (Min)	570 (Max)

Distributor

**Gilbert Curry
Industrial Plastics Co Ltd**

Tel: 024 76 588 388

Fax: 024 76 588 389

email: plastics@gcip.co.uk



Technical Specification

Property	ISO Methods	Units	NYLATRON® NSM
Colour	-	-	Grey
Density	1183	g/cm ³	1.15
Water absorption			
Saturation in air (23°C / 50% RH)	-	%	2.00
Saturation in water (23°C)	-	%	6.30
Tensile strength* ¹	527	N/mm ²	76
Tensile modulus of elasticity* ¹	527	N/mm ²	3100
Elongation at break* ¹	527	%	25
Impact - Charpy* ¹	179/1eU	kJ/m ²	>100
Impact - Izod notched* ¹	180/2A	kJ/m ²	4
Hardness	Rockwell	-	M81
	Shore D	-	-
Melt point	-	°C	220
Max allowable service temp in air			
for short periods	-	°C	165
continuously for 20,000hrs	-	°C	90
Linear thermal expansion coefficient	-	K ⁻¹ x 10 ⁻⁵	8.0
Thermal conductivity	-	W/(K.m)	0.29
Flammability* ² (6mm thickness)	-	-	HB
Volume resistivity* ¹	IEC93	Ohm.cm	>10 ¹⁴
Dielectric strength* ¹	IEC243	kV/mm	25
Outside applications - UV resistance	-	-	B
Acids - strong (pH < 3)	-	-	C
Alkalis - strong (pH > 11)	-	-	B/C
Chlorinated hydrocarbons	-	-	A/B
Hot water	-	-	B

'A' - Acceptable service; 'B' - Limited service; 'C' - Unacceptable.

*¹ Measured on dry test specimens (where applicable)

*² Tests completed by Quadrant EPP, using UL test methods

Not all material sizes shown within the delivery programme section of this data sheet are available as standard. Please contact Quadrant EPP UK Ltd for further details.

The data shown are typical values and are not intended to represent specifications. Their aim is to guide the user toward a material choice.