

# QUADRANT EPP PRODUCT DATA SHEET

## KETRON® PEEK-CA30

May 1999

*Polyetheretherketone CA30 (PEEK+ 30% Carbon)*

KETRON® PEEK-CA30 offers higher stiffness and strength than both KETRON® PEEK-1000 and KETRON® PEEK-HPV. In addition it has superior long term creep properties at elevated temperatures of up to 250°C. These features make KETRON® PEEK-CA30 ideal for applications involving high static loads.

- Excellent chemical resistance
- Excellent hydrolysis resistance
- High flammability rating
- Outstanding dimensional stability
- Wide operating range (-20°C to +250°C)
- Electrostatic dissipative properties
- Excellent mechanical strength / stiffness
- Exceptional wear resistance

Common applications: Pump components; Valve seats; Bearings; Rollers; Gears; High temperature insulation; Components in boiling water or steam.

### Delivery Programme

Rod 500mm long			
Diameter (mm):	60 (Min)	80 (Max)	
Rod 1m long			
Diameter (mm):	6 (Min)	80 (Max)	
Rod 3m long			
Diameter (mm):	6 (Min)	60 (Max)	
Plate 500mm, 1m & 3m long			
Width (mm):	525		
Thickness (mm):	5 (Min)	8 (Max)	
Plate 500mm & 1m long			
Widths (mm):	305 & 625		
Thickness (mm):	10 (Min)	60 (Max)	
Plate 3m long			
Widths (mm):	305 & 625		
Thickness (mm):	10 (Min)	25 (Max)	
Tube 1m & 3m long			
O.D. (mm):	50 (Min)	200 (Max)	
I.D. (mm):	30 (Min)	160 (Max)	

### Distributor

**Gilbert Curry  
Industrial Plastics Co Ltd**

Tel: 024 76 588 388

Fax: 024 76 588 389

email: [plastics@gcip.co.uk](mailto:plastics@gcip.co.uk)



### Technical Specification

Property	ISO Methods	Units	KETRON® PEEK-CA30
Colour	-	-	Black
Specific gravity	1183	g/cm <sup>3</sup>	1.41
Water absorption			
Saturation in air (23°C / 50% RH)	-	%	0.14
Saturation in water (23°C)	-	%	0.30
Tensile strength* <sup>1</sup>	527	N/mm <sup>2</sup>	130
Tensile modulus of elasticity* <sup>1</sup>	527	N/mm <sup>2</sup>	7700
Elongation at break* <sup>1</sup>	527	%	5
Impact - Charpy* <sup>1</sup>	179/1eU	kJ/m <sup>2</sup>	35
Impact - Charpy notched* <sup>1</sup>	179/1eA	kJ/m <sup>2</sup>	4
Hardness	Rockwell	-	M102
	Shore D	-	-
Melt Point	-	°C	340
Max allowable service temp in air			
for short periods	-	°C	310
continuously for 20000hrs	-	°C	250
Linear thermal expansion coefficient	-	K <sup>-1</sup> x 10 <sup>-5</sup>	2.5
Thermal Conductivity	-	W/(K.m)	0.92
Flammability* <sup>2</sup> (3mm thickness)	-	-	V-0
Volume Resistivity* <sup>1</sup>	IEC93	Ohm.cm	10 <sup>5</sup>
Dielectric Strength* <sup>1</sup>	IEC243	kV/mm	-
Outside applications - UV resistance	-	-	A
Acids - Strong (pH < 3)	-	-	A
Alkalis - Strong (pH > 11)	-	-	A
Chlorinated Hydrocarbons	-	-	A
Hot Water	-	-	A

'A' - Acceptable service; 'B' - Limited service; 'C' - Unacceptable.

\*<sup>1</sup> Measured on dry test specimens (where applicable)

\*<sup>2</sup> Tests completed by Quadrant EPP, using UL test methods

Not all material sizes shown within the delivery programme section of this data sheet are available as standard. Please contact Quadrant Engineering Plastic Products UK for further details.

The data shown are typical values and are not intended to represent specifications. Their aim is to guide the user toward a material choice.